

## SEVENTH QUARTERLY REPORT

AD A 069395

MANUFACTURING METHODS AND TECHNOLOGY PROJECT TO  
ESTABLISH PRODUCTION TECHNIQUES TO MANUFACTURE  
RIGID ARMOR FOR RADAR ANTENNA HARDENING

LEVEL


A067888

## REPORT PERIOD

1 DECEMBER 1978 TO 28 FEBRUARY 1979

DDC FILE COPY.

TECHNICAL SUPPORT DIRECTORATE  
UNITED STATES ARMY ELECTRONICS  
RESEARCH AND DEVELOPMENT COMMAND  
FORT MONMOUTH, NEW JERSEY



PREPARED UNDER CONTRACT NO. DAAB07-77-C-0476

Approved for public release; distribution unlimited.

PREPARED BY

**SWEDLOW, INC.**

12122 Western Avenue, Garden Grove, California 92645

79 06 04 110

### NOTICES

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Destroy this report when it is no longer needed. Do not return it to originator.

This project has been accomplished as part of the US Army Manufacturing Methods and Technology Program which has as its objective the timely establishment of manufacturing processes, techniques or equipment to insure the efficient production of current or future defense programs.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) MANUFACTURING METHODS AND TECHNOLOGY (MM&T) PROJECT TO ESTABLISH PRODUCTION TECHNIQUES TO MANUFACTURE RIGID ARMOR FOR RADAR ANTENNA HARDENING		5. TYPE OF REPORT & PERIOD COVERED Seventh Quarterly Report, on 1 Dec 1978 - 28 Feb 1979
6. AUTHOR R./Doerr		7. PERFORMING ORG. REPORT NUMBER
8. PERFORMING ORGANIZATION NAME AND ADDRESS SWEDLOW, Inc. 12122 Western Avenue Garden Grove, CA 92645		9. CONTRACT OR GRANT NUMBER(s) Contract No. DAAB07-77-C-0476
10. CONTROLLING OFFICE NAME AND ADDRESS TECHNICAL SUPPORT DIRECTORATE U.S. ARMY ELECTRONICS RESEARCH & DEVELOPMENT CMD FORT MONMOUTH, NEW JERSEY		11. REPORT DATE March 1979
12. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) 29 p		13. NUMBER OF PAGES 22
14. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		15. SECURITY CLASS (of this report) UNCLASSIFIED
16. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		17. DECLASSIFICATION/DOWNGRADING SCHEDULE
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Armor Panel Polymeric Radar Antenna Hardening		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  (See reverse side)		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

Block No. 20

ABSTRACT

This program is being conducted to establish production techniques and production capabilities for manufacture of plastic armor panels intended to provide ballistic protection for flat radar antennae.

Technical fabrication problems were reassessed and subscale process development initiated to solve these problems.

Subscale panels, fabricated during the period, demonstrated progress in the elimination of several of the processing problems. Overall panel opacity, surface delaminations, and voids or trapped air were brought under control.

The reduction of preconditioning temperatures to less than 180°F and a reduction of the lamination time eliminated the opacity problem.

Application of a woven polypropylene fabric as protective face plies eliminated the surface delamination or non-lamination problem on the limited number of samples fabricated this period.

The utilization of silicone sponge rubber seals improved the degassing efficiency and evacuation capabilities during processing. Minimal voids or air entrapment were the result.

The process revisions required to accomplish the above were defined.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

## SEVENTH QUARTERLY REPORT

MANUFACTURING METHODS AND TECHNOLOGY PROJECT TO  
ESTABLISH PRODUCTION TECHNIQUES TO MANUFACTURE  
RIGID ARMOR FOR RADAR ANTENNA HARDENING

## REPORT PERIOD

1 DECEMBER 1978 TO 28 FEBRUARY 1979

TECHNICAL SUPPORT DIRECTORATE  
UNITED STATES ARMY ELECTRONICS  
RESEARCH AND DEVELOPMENT COMMAND  
FORT MONMOUTH, NEW JERSEY

PREPARED UNDER CONTRACT NO. DAAB07-77-C-0476

Approved for public release; distribution unlimited.

PREPARED BY

**SWEDLOW, INC.**

12122 Western Avenue, Garden Grove, California 92645

Accession For	
1. G. & I.	<input checked="" type="checkbox"/>
2. B	<input type="checkbox"/>
3. and	<input type="checkbox"/>
4. and	<input type="checkbox"/>
5. and	
6. and	
7. and	
8. and	
9. and	
10. and	
11. and	
12. and	
13. and	
14. and	
15. and	
16. and	
17. and	
18. and	
19. and	
20. and	
21. and	
22. and	
23. and	
24. and	
25. and	
26. and	
27. and	
28. and	
29. and	
30. and	
31. and	
32. and	
33. and	
34. and	
35. and	
36. and	
37. and	
38. and	
39. and	
40. and	
41. and	
42. and	
43. and	
44. and	
45. and	
46. and	
47. and	
48. and	
49. and	
50. and	
51. and	
52. and	
53. and	
54. and	
55. and	
56. and	
57. and	
58. and	
59. and	
60. and	
61. and	
62. and	
63. and	
64. and	
65. and	
66. and	
67. and	
68. and	
69. and	
70. and	
71. and	
72. and	
73. and	
74. and	
75. and	
76. and	
77. and	
78. and	
79. and	
80. and	
81. and	
82. and	
83. and	
84. and	
85. and	
86. and	
87. and	
88. and	
89. and	
90. and	
91. and	
92. and	
93. and	
94. and	
95. and	
96. and	
97. and	
98. and	
99. and	
100. and	
101. and	
102. and	
103. and	
104. and	
105. and	
106. and	
107. and	
108. and	
109. and	
110. and	
111. and	
112. and	
113. and	
114. and	
115. and	
116. and	
117. and	
118. and	
119. and	
120. and	
121. and	
122. and	
123. and	
124. and	
125. and	
126. and	
127. and	
128. and	
129. and	
130. and	
131. and	
132. and	
133. and	
134. and	
135. and	
136. and	
137. and	
138. and	
139. and	
140. and	
141. and	
142. and	
143. and	
144. and	
145. and	
146. and	
147. and	
148. and	
149. and	
150. and	
151. and	
152. and	
153. and	
154. and	
155. and	
156. and	
157. and	
158. and	
159. and	
160. and	
161. and	
162. and	
163. and	
164. and	
165. and	
166. and	
167. and	
168. and	
169. and	
170. and	
171. and	
172. and	
173. and	
174. and	
175. and	
176. and	
177. and	
178. and	
179. and	
180. and	
181. and	
182. and	
183. and	
184. and	
185. and	
186. and	
187. and	
188. and	
189. and	
190. and	
191. and	
192. and	
193. and	
194. and	
195. and	
196. and	
197. and	
198. and	
199. and	
200. and	
201. and	
202. and	
203. and	
204. and	
205. and	
206. and	
207. and	
208. and	
209. and	
210. and	
211. and	
212. and	
213. and	
214. and	
215. and	
216. and	
217. and	
218. and	
219. and	
220. and	
221. and	
222. and	
223. and	
224. and	
225. and	
226. and	
227. and	
228. and	
229. and	
230. and	
231. and	
232. and	
233. and	
234. and	
235. and	
236. and	
237. and	
238. and	
239. and	
240. and	
241. and	
242. and	
243. and	
244. and	
245. and	
246. and	
247. and	
248. and	
249. and	
250. and	
251. and	
252. and	
253. and	
254. and	
255. and	
256. and	
257. and	
258. and	
259. and	
260. and	
261. and	
262. and	
263. and	
264. and	
265. and	
266. and	
267. and	
268. and	
269. and	
270. and	
271. and	
272. and	
273. and	
274. and	
275. and	
276. and	
277. and	
278. and	
279. and	
280. and	
281. and	
282. and	
283. and	
284. and	
285. and	
286. and	
287. and	
288. and	
289. and	
290. and	
291. and	
292. and	
293. and	
294. and	
295. and	
296. and	
297. and	
298. and	
299. and	
300. and	
301. and	
302. and	
303. and	
304. and	
305. and	
306. and	
307. and	
308. and	
309. and	
310. and	
311. and	
312. and	
313. and	
314. and	
315. and	
316. and	
317. and	
318. and	
319. and	
320. and	
321. and	
322. and	
323. and	
324. and	
325. and	
326. and	
327. and	
328. and	
329. and	
330. and	
331. and	
332. and	
333. and	
334. and	
335. and	
336. and	
337. and	
338. and	
339. and	
340. and	
341. and	
342. and	
343. and	
344. and	
345. and	
346. and	
347. and	
348. and	
349. and	
350. and	
351. and	
352. and	
353. and	
354. and	
355. and	
356. and	
357. and	
358. and	
359. and	
360. and	
361. and	
362. and	
363. and	
364. and	
365. and	
366. and	
367. and	
368. and	
369. and	
370. and	
371. and	
372. and	
373. and	
374. and	
375. and	
376. and	
377. and	
378. and	
379. and	
380. and	
381. and	
382. and	
383. and	
384. and	
385. and	
386. and	
387. and	
388. and	
389. and	
390. and	
391. and	
392. and	
393. and	
394. and	
395. and	
396. and	
397. and	
398. and	
399. and	
400. and	
401. and	
402. and	
403. and	
404. and	
405. and	
406. and	
407. and	
408. and	
409. and	
410. and	
411. and	
412. and	
413. and	
414. and	
415. and	
416. and	
417. and	
418. and	
419. and	
420. and	
421. and	
422. and	
423. and	
424. and	
425. and	
426. and	
427. and	
428. and	
429. and	
430. and	
431. and	
432. and	
433. and	
434. and	
435. and	
436. and	
437. and	
438. and	
439. and	
440. and	
441. and	
442. and	
443. and	
444. and	
445. and	
446. and	
447. and	
448. and	
449. and	
450. and	
451. and	
452. and	
453. and	
454. and	
455. and	
456. and	
457. and	
458. and	
459. and	
460. and	
461. and	
462. and	
463. and	
464. and	
465. and	
466. and	
467. and	
468. and	
469. and	
470. and	
471. and	
472. and	
473. and	
474. and	
475. and	
476. and	
477. and	
478. and	
479. and	
480. and	
481. and	
482. and	
483. and	
484. and	
485. and	
486. and	
487. and	
488. and	
489. and	
490. and	
491. and	
492. and	
493. and	
494. and	
495. and	
496. and	
497. and	
498. and	
499. and	
500. and	
501. and	
502. and	
503. and	
504. and	
505. and	
506. and	
507. and	
508. and	
509. and	
510. and	
511. and	
512. and	
513. and	
514. and	
515. and	
516. and	
517. and	
518. and	
519. and	
520. and	
521. and	
522. and	
523. and	
524. and	
525. and	
526. and	
527. and	
528. and	
529. and	
530. and	
531. and	
532. and	
533. and	
534. and	
535. and	
536. and	
537. and	
538. and	
539. and	
540. and	
541. and	
542. and	
543. and	
544. and	
545. and	
546. and	
547. and	
548. and	
549. and	
550. and	
551. and	
552. and	
553. and	
554. and	
555. and	
556. and	
557. and	
558. and	
559. and	
560. and	
561. and	
562. and	
563. and	
564. and	

## ABSTRACT

This program is being conducted to establish production techniques and production capabilities for manufacture of plastic armor panels intended to provide ballistic protection for flat radar antennae.

Technical fabrication problems were reassessed and subscale pro-cell development initiated to solve these problems.

Subscale panels, fabricated during the period, demonstrated progress in the elimination of several of the processing problems. Overall panel opacity, surface delaminations, and voids or trapped air were brought under control.

The reduction of preconditioning temperatures to less than 180°F and a reduction of the lamination time eliminated the opacity problem.

Application of a woven polypropylene fabric as protective face plies eliminated the surface delamination or non-lamination problem on the limited number of samples fabricated this period.

The utilization of silicone sponge rubber seals improved the degassing efficiency and evacuation capabilities during processing. Minimal voids or air entrapment were the result.

The process revisions required to accomplish the above were defined.

## CONTENTS

<u>SECTION</u>	<u>TITLE</u>	<u>PAGE</u>
1.0	PURPOSE . . . . .	1
2.0	INTRODUCTION . . . . .	2
3.0	PROCESS DEVELOPMENT . . . . .	3
3.1	General . . . . .	3
3.2	Defect Causes - Corrective Action . . . . .	3
4.0	PANEL FABRICATION . . . . .	9
4.1	Woven Polypropylene Fabric . . . . .	9
4.2	Pressure Pads . . . . .	11
4.3	Molding Procedure . . . . .	11
5.0	SILICONE SPONGE RUBBER SEALS . . . . .	16
5.1	Seal Materials . . . . .	16
5.2	Seal Design . . . . .	16
6.0	PROBLEM AREAS . . . . .	21
6.1	Program Schedule Revisions . . . . .	21
6.2	Remaining Technical Problems . . . . .	21
7.0	PROGRAM FOR NEXT PERIOD . . . . .	22
7.1	Schedule Revision . . . . .	22
7.2	Full Scale Seals . . . . .	22
7.3	Subscale Process Development . . . . .	22
7.4	Full Scale Process Development . . . . .	22

## 1.0 PURPOSE

The purpose of this program is to establish production techniques and production capabilities for the manufacture of armor panels. The armor panels are intended for use with flat radar antennae to provide protection from munitions fragments.

The armor panels will be flat molded sheets of various sizes and edge finishes. The sheets will be molded from cross-ply assemblies of unidirectionally oriented, blown film made from a dielectric grade polypropylene. A protective over-layer will be molded into the panel surfaces and camouflage will be incorporated in or onto a portion of the panels.

The program is divided into four tasks as described below:

### Step 1 Engineering Samples

Two sets of two each panels will be produced in order to demonstrate the ballistic capabilities of the selected materials and processes.

### Step 2 Confirmatory Samples

Ten sets of two each panels of various sizes, thicknesses, and camouflaging methods will be produced in order to demonstrate the total capabilities of the panels in regards to environmental stability, electronic transmission, and ballistic characteristics. In addition, camouflaging techniques and panel trim and edge fusing will be demonstrated.

### Step 3 Pilot Run

Thirty-two sets of two each panels will be produced in order to demonstrate the capacity of each production step and verify the capability of the line to fabricate at an acceptable rate.

### Step 4 Production Capability Demonstration

An in-plant demonstration will be held in order to show the production capabilities of the pilot production line to invited representatives of industry and government.

The first quarterly report described in detail the program objectives, tasks, and schedule.

## 2.0 INTRODUCTION

The following report covers the period from December 1, 1978 to February 28, 1979.

During this period the technical problems encountered during the program were reassessed and subscale process development initiated to solve them.

The subscale panels fabricated during this period demonstrated progress in the elimination of overall opacity, surface defects, and elimination of voids or trapped air. Remaining development problems include elimination of striations (stress whitening) thickness and warpage control and a scale-up of the processes.

In the following section the various defects encountered during the program are discussed. Methods employed to correct these defects are presented.

Process steps used to produce panels during this period are described as is the latest seal configuration developed for the revised process.

### 3.0 PROCESS DEVELOPMENT

#### 3.1 General

During the last period, full scale panels were fabricated in both 3/8-inches and 1-inch thickness. The panels exhibited major surface and minor subsurface defects. A revised procedure employed in subscale process development during this same period improved control of several of these defect areas.

##### Panel Defects

- Surface whiteness and panel opacity
- Surface and subsurface delaminations
- Voids and/or trapped air pockets
- Whitish striations (stress whitening)
- Nominal thickness and thickness tolerance variations
- Warpage

During the last period surface whiteness and opacity was eliminated by reducing the temperature of all preconditioning steps to less than 180°F. Surface and subsurface delamination defects were decreased by the above change and a solvent prewash of the protective film. However, surface delaminations remained an intermittently recurring problem when using balanced film protective cover plies such as Hercules B-500.

Voids and/or trapped air pockets and the whitish striations remained unsolved problems last period. Thickness and warpage control techniques were also not fully determined.

#### 3.2 Defect Causes - Corrective Action

In order to attempt to solve processing problems, a theory of the probable defect causes is defined and corrective action taken or proposed is discussed below.

##### Surface Whitening and Panel Opacity

Although in some isolated cases panel opacity may be caused by contamination, the major causes appear to be orientation release of the oriented film during pre-conditioning or over heat of the panel during the lamination cycle. The orientation release temperature being pressure related occurs at a relatively low

temperature during the preconditioning when the film is subjected to vacuum pressure only.

Panel opacity occurs during lamination at temperatures over 350°F and is temperature-time related. Rapid discoloration occurs at temperatures over 355°F and much more slowly below 355°F.

#### Corrective Action

Reduction of all preconditioning temperatures to below 180°F and the decrease of lamination time at the upper temperatures has eliminated the opacity problem in all 3/8-inch thick panels fabricated during this period.

#### Surface and Subsurface Delaminations

Contaminants such as film lubricants, oil from film handling, and air or moisture trapped between plies are examples of introduced contamination that cause both surface and subsurface delamination. In addition, integral material modifiers such as plasticizers, stabilizers, non blockers, found in protective films can also cause delamination or non-lamination.

Thermal gradients that occur during panel cool down are also believed to induce shear stresses that may jeopardize the panel laminations. Severe in-plane stresses develop at the panel surfaces due to contraction of the outer surfaces during cool down and the restriction of this contraction by the still hot interior.

#### Corrective Action

Decreasing the number of protective film plies, solvent cleaning these plies, and cutting them undersize to the panel decreased surface delaminations when using thin balanced oriented film as protective surface materials. However, these results did not entirely eliminate the surface problems suggesting that integral contamination and/or the inability of the film to cope with in-plane surface motions was, on occasion, causing surface delamination.

During this period a woven polypropylene fabric, Propex Style I-89 was incorporated as a protective surfacing material. This material manufactured by AMOCO Fabrics Company of Atlanta, Georgia shows promise as a solution to the surface lamination problem. In addition, the woven material provides superior surface integrity due to its interwoven nature and incorporates an ultra-violet stabilizer that should improve panel weathering characteristics.

### Voids and/or Trapped Air Pockets

Panels fabricated during the last period showed marked improvements as noted in the above sections. The voids or trapped air problem, however, was not significantly improved, although some panels fabricated this period were essentially void free.

The multi-ply nature of the prelaminated film stack presents a very large intra-ply area of trapped air that must be eliminated. Film overlaps and film winding spaces provide natural pockets and seal off areas that tend to prevent void elimination by pressure alone. Any surface moisture pick-up by the film must also be eliminated in order to prevent outgassing during the high temperature lamination process.

### Corrective Action

Two major processing step changes were employed in the void free panels fabricated during this period as compared with process used in fabrication of the less successful panels last period. One change involved the allowable leakage employed during the two periods. Although a minimum 29-inch Hg vacuum was used during both periods, the leakage allowable (as measured by the vacuum drop with the evacuated assembly closed off) was reduced. Last period a vacuum drop of two-inches Hg within a five minute period was allowed. During this period, the maximum drop within a ten minute period was limited to one-inch Hg. This represents an allowable volume leakage reduction to one-quarter of the previous control.

The second change involved the initial evacuation step and the preconditioning of the film stack. Employment of silicone sponge rubber seals (described in Section 5.0 and illustrated in Figures 8 and 9) allows for initial film stack compression simultaneously with evacuation. Additionally, the compressive resistance of the seal limits the stack compression and leaves a somewhat loose stack during the important moisture and air removal (preconditioning) cycle.

In a separate exploratory panel molding, thin rubber pads were placed between the flat rigid caul plates at both panel faces and the panel was laminated without the aid of evacuation. Resulting panels had only minimal air entrapment. This would indicate that a more uniform application of pressure as accomplished by use of the rubber pads is effective in elimination of voids and offers a possible alternate, lower cost processing method that may be suitable for some applications.

### Whitish Striations (Stress Whitening)

Striations of whitish discolorations occur to a greater or lesser

extent in most panel laminated using rigid metal caul plates. The striations, located in the central region, follow the film winding pattern and intersect at right angles. The most severe discolorations occur at the striation intersections. There seems to be a repeating pattern that occurs on about 2 1/2-inch centers as shown below in Figure 1. This pattern may be characteristic of a single mandrel winding or setting.




Figure 1. STRIATION PATTERN

It is surmised that the striations are caused by a buildup of ply overlaps that cause local high pressure zones that initiate the stress whitening. Figure 2 below illustrates overlap buildups that would cause a striation. It is obvious that at striation intersections the ply buildup is additive and therefore most severe.



Figure 2. OVERLAP ILLUSTRATION

This condition could either be the result of a repeating pattern or random highs and lows resulting from a random winding pattern. The central panel location of the defect is consistent with edge related flow and restricted flow in the plane form central region.

As noted in the previous section, a limited experiment was conducted wherein a rubber face sheet was used in an attempt to relieve high local stress areas and more uniformly distribute applied pressures. Surface flatness control was, of course, poor but there was no appearance of the whitish striations.

#### Corrective Action

As noted above a rubber pressure distribution pad eliminates the striations. The resulting surface distortion on both sides varies from the flat plane up to 0.015-inches when using a 1/32-inch thick silicone rubber pad on both faces of a 3/8-inch thick panel. Examination of a limited number of tries showed that a single ply of woven polypropylene fabric Propex I-89 protective face ply appeared to decrease but not eliminate the problem.

Multiple plies of I-89 fabric on the panel faces or a combination of very thin pressure distribution pads with protective surface plies I-89 are possibilities that have not yet been tried.

Investigation of cross-ply winding techniques in pursuit of greater winding uniformity would be beneficial.

#### Nominal Thickness and Thickness Tolerance Variations

Control of panel thickness has been attempted by two different methods, loose stack thickness measurements and loose stack weights. Using either method, the resulting panel thickness is dependent on the pressure, temperature, and time variables of the lamination cycle. In addition, however, the degree of local overlap buildup (the mechanism that causes the striation discussed in the previous section) also affects final thickness. Increased local overlaps will tend to produce increased thickness.

Thickness tolerance ranges to date have been random with the two following exceptions. When molding between flat metal caul plates the laminated panels are consistently thicker in the mid panel region. Panels molded using a rubber pressure pad have random thicknesses across the panel and a smaller tolerance zone. These results are again consistent with restricted flow in the panel central region.

### Corrective Action

Thickness control is expected to improve as procedures are fixed. In addition, any method of control or minimization of the effect of the local buildup problem should make thickness control easier.

Other methods of measuring loose film stacks to provide thickness control information should be tried. One possibility would be loose film thickness measurements between flat plates at some given pressure.

### Warpage

Panel warpage has been attributed to two processing effects. Panel edge restrictions or edge pressure during laminating and differential temperatures between the panel faces during cool down result in warpage.

### Corrective Action

Present processing procedures, as described in the following section, avoid any panel edge pressure during the lamination cycle. This eliminates warpage from this cause but also precludes net panel edge molding.

Control of face temperature during cool down is a function of the laminating equipment platens, equipment controls, and tooling. Some difficulty has been encountered in control of these temperatures due to differences in press platen mass and variations in cooling passage flow rates. Selective adjustment in cooling fluid flow rates are being investigated as a control method in this area.

Lightly clamping panels against flat plates during the 200°F heat treat removes a portion of the panel warpage.

#### 4.0 PANEL FABRICATION

During this period several panels were fabricated using silicone sponge rubber seals. The fabrication procedures employed were essentially the same as that developed during the end of the last period with the incorporation of revisions discussed in the previous section.

In addition to creating the vacuum chamber between caul plates with sponge rubber seals, the allowable vacuum chamber leakage was reduced, and the woven polypropylene fabric protective face plies were incorporated. Panels were fabricated using caul plates only and both silicone rubber and teflon pressure pads.

A schematic of the processing steps is shown in Figure 3.

#### 4.1 Woven Polypropylene Fabric

A woven polypropylene fabric was successfully employed as a protective surface material in several subscale panel laminations. In all cases, the panel surfaces were without delamination or other defects.

When molded against flat metal caul plates, the woven fabric produced a smooth even surface with the fabric weave barely discernible. When molded using a flexible surface pad, the fabric pattern was accentuated and noticeably visible but still fused together in a continuous face ply.

The material used was Propex Style 1-89 woven polypropylene fabric. This material is manufactured by AMOCO Fabric Company, Patchogue Plymouth Division, Atlanta, Georgia. Some of the properties are noted below:

Tensile Strength	ASTM-1682	275 x 230 lbs/inch
UV Resistance, Strength Retention	FTMS No. 191 Method 5304 1000 Hours	>70 percent
Weight		6.0 oz/sq yd

The material is presently available in pigmented configuration only and contains an ultra-violet stabilizer.

The pigmentation increases surface opacity and masks off the smaller subsurface defects. Examination of the subsurface using a strong background light showed that the striation pattern was still in evidence on non pad augmented moldings.




Figure 3. FLOW DIAGRAM

Figure 5 "Woven Polypropylene Face Ply Lamination" describes the molding assembly and the molding cycle used to fabricate these panels.

#### 4.2 Pressure Pads

Two of the subscale panels fabricated during this period employed 1/32" silicone rubber pressure pads. One panel was laminated entirely without vacuum while the other employed the latest vacuum seal design and high vacuum throughout the cycle.

The resulting panels were both translucent and without striations or any whitish opaque areas. The evacuated panel was almost without voids or trapped air pockets while the non-evacuated panel contained only small and mostly edge associated voids.

Figure 6 "Rubber Pad Lamination" illustrates this method of lamination using both rubber pad and panel evacuation.

A 1/16-inch thick teflon (TFE) pressure pad was used on the faces of another of the subscale panel moldings. The resulting surface irregularities were much less pronounced than those obtained when using 1/32-inch thick rubber pads. However, the teflon "cold flowed" under the high molding pressures causing panel edge distortion problems. This problem coupled with the high cost of the material would seem to eliminate teflon as a practical pressure pad material.

Figure 7 "Teflon Pad Lamination" illustrates the use of teflon pads while laminating.

#### 4.3 Molding Procedure

The panel laminations were all preceded by a vacuum seal evaluation followed by an oven preconditioning cycle.

Prior to molding, the evacuated assembly was checked by closing off the chamber for 10 minutes and noting vacuum gauge drop. A drop to no less than 29-inches Hg indicates a satisfactorily sealed assembly. The vacuum was maintained throughout the lamination process.


Panels were then preconditioned to remove air and moisture at 160-180°F while under vacuum.

The panel was then ready for the press lamination cycle. Constant pressure and full vacuum were maintained throughout this cycle.

The lamination procedure chosen was intended to accomplish the following:

- Maintain preconditioning temperature well below orientation release temperature
- Maintain high vacuum throughout process (where applicable)
- Effect rapid heat-up during molding - slowing only near maximum temperature to prevent temperature over shoot
- Effect rapid cool down while attempting to minimize temperature differences between panel face to face and face to mid-panel.

The temperature and pressure control are defined in Figure 4 below:



Symbols:

T = Temperature

t = time

Subscripts:

r = rise


d = dwell

f = fall

Figure 4

Illustrations (Figures 5, 6 and 7) describe the laminating assembly and procedures used to fabricate the various panels fabricated during this period.


# LAMINATING ASSEMBLY



## LAMINATION CYCLE

Initial vacuum check		Vacuum drop to 29.7-inches Hg in 10 minutes
Preconditioning		15 hours at 170°F at 29-30-inches Hg
Heatup time (Room temperature to 350°F)	$t_r$	60 minutes (mid panel)
Dwell time (Time at or above 350°F)	$t_d$	5 minutes (mid panel)
Cool down time (350°F to room temperature)	$t_f$	70 minutes (mid panel)
Maximum temperature	$T_{max}$	352°F (mid panel)
Maximum temperature differential		
Face to Face	$\Delta T_1$	19°F
Face to mid panel	$\Delta T_2$	23°F
Pressure	P	2200 psi
Vacuum		30-inches Hg


Figure 5. NOVEN POLYPROPYLENE FACE PLY LAMINATION



#### LAMINATION CYCLE

Initial vacuum check		Vacuum drop to 25.5-inches in 10 minutes
Preconditioning		15 hours at 170°F and 29-20-inches Hg
Heatup time (Room temperature to 350°F)	$t_r$	60 minutes (mid panel)
Dwell time (Time at or above 350°F)	$t_d$	5 minutes (mid panel)
Cool down time (350°F to room temperature)	$t_f$	75 minutes (mid panel)
Maximum temperature	$T_{max}$	352°F
Maximum temperature differential		
Face to Face	$\Delta T_1$	9°F
Face to mid panel	$\Delta T_2$	18°F
Pressure	P	2200 psi
Vacuum		30-inches Hg

Figure 6. RUBBER PAD LAMINATION



#### LAMINATION CYCLE

Initial vacuum check	Vacuum drop to 29.0-inches Hg in 10 minutes	
Preconditioning	15 hours at 170°F and 29-30-inches Hg	
Heatup time (Room temperature to 350°F)	$t_r$	67 minutes (mid panel)
Dwell time (Time at or above 350°F)	$t_d$	3 minutes (mid panel)
Cool down time (350°F to room temperature)	$t_f$	70 minutes (mid panel)
Maximum temperature	$T_{max}$	351°F (mid panel)
Maximum temperature differential		
Face to Face	$\Delta T_1$	10°F
Face to mid panel	$\Delta T_2$	19°F
Pressure	P	2200 psi
Vacuum	30-inches Hg	

Figure 7. TEFLON PAD LAMINATION

## 5.0 SILICONE SPONGE RUBBER SEALS

During this period sponge rubber seal materials were evaluated. The best performer was selected and fabricated into subscale seals. The seals were evaluated during panel fabrication and then redesigned to a more optimum configuration.

### 5.1 Seal Materials

Four silicone sponge rubber seal materials were evaluated. Two of the materials are specification manufactured to AMS 3195 TE12 and AMS 3195 TE 18. The other materials were Connecticut Hard Rubber products COHR-10470 and COHR-10480.

Testing at various degrees of compression and at molding cycle temperatures showed that seal compression must be held under 50 percent if the seal is to have multi cycle possibilities. The COHR-10480 material demonstrated superior performance due to its lower compressive set characteristics.

### 5.2 Seal Design

The silicone sponge rubber seal is required to make a vacuum seal between the caul plates at the loose stack height and then to compress to final molding thickness.

In order to do this and limit the seal compression to less than 50 percent, seals are used in conjunction with internal caul plates. Figures 8 and 9 "Seal Compression" show the loose stack as initially captured and the seal in its final compressed state.

Figures 10 and 11 show the proposed full scale seal design. The three-inch high seal (Figure 9) requires two 1/8-inch thick aluminum frames in order to prevent collapse during evacuation.

PREPARED BY A. D. WIL	SWEDLOW Inc.	PAGE NO 17 OF
CHECKED BY		REPORT NO.
DATE		CUSTOMER ERADIC. CO.




Figure 8. SEAL COMPRESSION - 3/8-Inch PANEL

PREPARED BY M. J. P. A.	SWEDLOW Inc.	PAGE NO 18 OF
CHECKED BY		REPORT NO.
DATE	SEAL COMPRESSION 1" PANEL	CUSTOMER ERADCOM





Figure 9. SEAL COMPRESSION - 1-Inch PANEL



SCALE FULL

Figure 10. SEAL -  $\frac{3}{8}$ " x 24" x 34" PANEL



6.0 PROBLEM AREAS

6.1 Program Schedule Revisions

As the objectives of this program have not been achieved within the originally scheduled time period, a major program rescheduling is required.

6.2 Remaining Technical Problems

Although surface condition problems, trapped air/voids, and overall panel opacity problems appear to be under control using the latest processing procedures, the striations (stress whitening) thickness control and warpage control require further investigation.

7.0 PROGRAM FOR NEXT PERIOD

7.1 Schedule Revision

Prepare and present a revised scheme for overcoming the technical problems and reschedule the program in accordance with this plan.

7.2 Full Scale Seals

Fabricate full scale silicone sponge rubber seal assemblies.

7.3 Subscale Process Development

Repeat successful processing procedures developed during this period in conjunction with the investigation of remaining technical problems.

7.4 Full Scale Process Development

Upon accomplishment of repeatable successful subscale panel fabrication, start investigation of scale-up problem.